



767 Chapman Lake Drive - Warsaw, Indiana 46582

**Product Data Sheet**

<b>Product:</b> <u>ACLLAB50NA1</u>	<b>Description:</b> <u>50% DE Antiblock PEC</u>
------------------------------------	---

***Product Highlights:***                                    ***Microscopically roughens film surfaces***  
***Prevents adhesion of films to one another***

**Carrier Resin Data**

Type	<u>Units</u>	<u>Value</u>	<u>Method</u>
		LLDPE	
<b>Melt Flow</b>	g/10min	20.0	ASTM D1238
<b>Density</b>	g/cm <sup>3</sup>	0.924	ASTM D792

**Concentrate Data**

	<u>Units</u>	<u>Value</u>	<u>Method</u>
<b>Additive Loading</b>	%	50.0	internal
<b>Melt Flow</b>	g/10min	5.0	ASTM D1238
<b>Pellet Weight</b>	Pellets/gm	50	internal
<b>Dispersion</b>		Film Grade	internal

**Regulatory Data**

<b><u>FDA</u></b>	The components in this product comply with the following sections of Title 21, Code of Federal Regulations (21CFR): 174.5                                    178.2010 177.1520                                    178.3297
<b><u>CONEG</u></b>	The components of this product are compliant with the current requirements issued by the Coalition of North Eastern Governors (CONEG) requiring less than 100 PPM total in the final product packaging.

*The above information is believed to be accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied, and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. This material is sold with the express understanding that our customers will conduct their own test to determine the suitability of the material for their particular application.*