



767 Chapman Lake Drive - Warsaw, Indiana 46582

**Product Data Sheet**

<b>Product:</b> <u>ACLLAS05NA1</u>	<b>Description:</b> <u>Antistat PEC</u>
------------------------------------	---

**Product Highlights:**

*Dissipates static charge on the surface  
High temperature stability  
High purity*

**Carrier Resin Data**

Type	<u>Units</u>	<u>Value</u>	<u>Method</u>
		LLDPE	
<b>Melt Flow</b>	g/10min	20.0	ASTM D1238
<b>Density</b>	g/cm <sup>3</sup>	0.926	ASTM D792

**Concentrate Data**

	<u>Units</u>	<u>Value</u>	<u>Method</u>
<b>Additive Loading</b>	%	5.0	internal
<b>Melt Flow</b>	g/10min	22.0	ASTM D1238
<b>Pellet Weight</b>	Pellets/gm	60	internal

**Regulatory Data**

<b><u>FDA</u></b>	The components of this product are approved by the FDA for safe use in Polyethylene food contact applications subject to specific restrictions. Please contact your Rainmaker Polymers Account Manager for additional information.
<b><u>CONEG</u></b>	The components of this product are compliant with the current requirements issued by the Coalition of North Eastern Governors (CONEG) requiring less than 100 PPM total in the final product packaging.

*The above information is believed to be accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied, and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. This material is sold with the express understanding that our customers will conduct their own test to determine the suitability of the material for their particular application.*