767 Chapman Lake Drive - Warsaw, Indiana 46582

Product Data Sheet

Product: ACLLPA03NA3 **Description:** 3% Processing Aid PEC

Product Highlights:

Reduces melt fracture
Increases machine thruputs
Savings in raw material costs

Carrier Resin Data

	Units	Value	Method
Type		LLDPE	
Melt Flow	g/10min	20.0	ASTM D1238
Density	g/cm^3	0.924	ASTM D792

Concentrate Data

	Units	Value	Method
Additive Loading	%	3.0	internal
Melt Flow	g/10min	18.0	ASTM D1238
Pellet Weight	Pellets/gm	65	internal

Regulatory Data

FDA The components in this product comply with the following sections of Title 21, Code of Federal Regulations (21CFR):
174.5 177.1520
Note: Max level of PA in final part may not exceed 0.22%

CONEG The components of this product are compliant with the current requirements issued by the Coalition of North Eastern Governors (CONEG) requiring less than 100 PPM total in the final product packaging.

The above information is believed to be accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied, and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. This material is sold with the express understanding that our customers will conduct their own test to determine the suitability of the material for their particular application.

5/1/2007