

767 Chapman Lake Drive - Warsaw, Indiana 46582

## **Product Data Sheet**

	Product:	ACLLSL05NA2	Description:	5% Slip PEC
--	----------	-------------	--------------	-------------

Product Highlights: Improves surface lubrication
Lowers coefficient of friction
Decreases film tact

## **Carrier Resin Data**

Туре	<u>Units</u>	<u>Value</u> LLDPE	<u>Method</u>
Melt Flow	g/10min	20.0	ASTM D1238
Density	g/cm <sup>3</sup>	0.925	ASTM D792

## **Concentrate Data**

Joniooninato Bata			
Additive Loading	<u>Units</u> %	<u>Value</u> 5.0	<u>Method</u> internal
Auditive Loading	70	5.0	interrial
Melt Flow	g/10min	20.0	ASTM D1238
Pellet Weight	Pellets/gm	60	internal
Dispersion		Film Grade	internal

## **Regulatory Data**

regulatory 2 atta			
<u>FDA</u>	The components in this product comply with the following sections of Title 21, Code of Federal Regulations (21CFR):		
	174.5 178.2010 177.1520		
<u>CONEG</u>	The components of this product are compliant with the current requirements issued by the Coalition of North Eastern Governors (CONEG) requiring less than 100 PPM total in the final product packaging.		

The above information is believed to be accurate and reliable. Because conditions of use are beyond our control, we make no warranties, expressed or implied, and specifically exclude any and all warranties of merchantability and fitness for a particular purpose. This material is sold with the express understanding that our customers will conduct their own test to determine the suitability of the material for their particular application.